

BLACK MASTERBATCHES TECHNOFIN®

Mark	Polymer base	Carbon black, %	Carbon black type	Filler	Bulk density, g/cm ³	MFI, g/10min 190°C	Application						
							PE and PP pipes	Blow moulding	PE and PP films	Thin PE films	Extrusion sheets	Injection molding	Cable insulation PVC
CPG 970	LLDPE	40	P-type		0,75±0,1	1-10 (10kg)	●	●	●	●	●	●	
CPG 980	LLDPE	30	P-type	Δ	0,75±0,1	1-10 (10kg)	●	●	●	○	●	●	
CPG 930	LDPE / LLDPE	30	HAF	Δ	0,75±0,1	0,5-3,0 (10 kg)		●	●	○	●	●	○
CPG 940	LLDPE	40	HAF	Δ	0,75±0,1	5-20 (21,6 kg)		●	●	○	●	●	○
CPG 960	LDPE / LLDPE	50	SRF		0,75±0,1	5-15 (21,6 kg)	●	○			●	○	
CPG 9021	LDPE / LLDPE	20	HAF	Δ	0,75±0,1	1-15 (21,6 kg)	●				○	○	
CPG 950	LDPE / LLDPE	30	HAF	Δ	0,75±0,1	1-5 (21,6 kg)	●	○	○	○	●	○	○

● – recommended

Δ – contains

○ – application possible after testing

Technocom LLC shall not be responsible for the use, accuracy and completeness of the information offered, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. Technocom LLC does not take any responsibility or liability for any information offered herein. The responsibility regarding the observance of third-party rights in the course of a subsequent processing and marketing of our products lies with the buyer.

